

June 2000

OceanMaster Everfill Epoxy Resin Filler

Description

High performance epoxy resin filler for general repair and fairing jobs. Excellent sanding and non sagging properties.

For use on

All marine and industrial applications for filling, repair and fairing work.. Forms a strong, permanent water proof filler that is easy to sand and will bond to a variety of substrates.

Direction for use

Product designed for application by spatula, putty knife or trowel.

Airless Spray	Line Pressure :	N/A
Conventional Spray	Pot Pressure :	N/A
Wet Film Thickness	:	N/A
Dry Film Thickness	:	N/A
Coverage	:	N/A
Mixing Ratio	:	2 to 1 by volume
Thinner	:	N/A
Recoat	:	4 hrs
Curing Time	:	8 hrs
Aged Recoat	:	Sand Surface
Finish	:	Light Brown

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.
