

June 2000

## **OceanMaster Marine Undercoat**

### Description

Surfacing undercoat with water resistance properties for above waterline applications. High opacity and good film build effectively hide substrate and level up minor surface imperfection.

### For use on

Boat hulls after fairing, steel and aluminium after priming, or directly on fibreglass and timber. Provides excellent base for OceanMaster Marine Gloss and other similar coatings.

### Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	:	N/A
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	90 microns
Dry Film Thickness	:	42 microns
Coverage	:	11 sq.m/L
Mixing Ratio	:	N/A
Thinner	:	T100 or T600
Drying Time	:	8 hrs
Recoat	:	16 hrs
Aged Recoat	:	Sand surface
Colour	:	Off White
Finish	:	Flat

### Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.

---