

June 2000

OceanMaster Polygloss Clear

Description

The ultimate two-pack polyurethane clear finish designed for application where a tough, durable glossy finish is required.

For use on

As a high gloss clear topcoat over a polyurethane coloured finish coat. Suitable for direct application to all new exotic timbers or over an epoxy two component timber preservative.

Direction for use

Product designed for application by spray or brush.

Airless Spray	Line Pressure :	100 – 130 Kg sq.cm
	Tip Size :	0.015 – 0.017
	Compression :	30:1
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	85 microns
Dry Film Thickness	:	40 microns
Coverage	:	11 to 12 sq.m/L
Mixing Ratio	:	3 to 1 by volume
Thinner	:	T300
Recoat	:	6 hrs min
Curing Time	:	48 hrs.
Aged Recoat	:	Sand Surface
Finish	:	Gloss

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.