

June 2000

OceanMaster Universal Primer

Description

Two pack epoxy primer designed as an anticorrosive coating to provide excellent adhesion and water resistance prior to the application of heavy duty epoxy coatings such as OceanMaster Everguard Epoxy Undercoat.

For use on

Suitable for steel and non-ferrous metals such as zinc, copper, bronze and aluminum.

Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	Line Pressure :	120 Kg sq.cm
	Tip Size :	0.015 – 0.021
	Fan Angle :	60 to 80 degrees
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	85 microns
Dry Film Thickness	:	40 microns
Coverage	:	9 sq.m/L
Mixing Ratio	:	3 to 1 by volume
Thinner	:	T500
Recoat	:	4 hrs min, 24 hrs max
Aged Recoat	:	Sand surface
Finish	:	Grey

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.