



OceanMaster Everguard Epoxy Undercoat

Description

Two-Pack epoxy undercoat for use above and below waterline. Suitable undercoat prior to the application of Polygloss finish and all OceanMaster antifouling.

For use on

Boat hulls after fairing, steel and aluminium after priming, or directly on fibreglass and timber. All marine situations prior to top coating or antifouling.

Direction for use

Product designed for application by airless, spray, roller or brush.

Airless Spray	Line Pressure :	120 Kg sq.cm
	Tip Size :	0.015 – 0.021
	Fan Angle :	60 to 80 degrees
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	100 microns
Dry Film Thickness	:	50 microns
Coverage	:	9 sq.m/L
Mixing Ratio	:	3 to 1 by volume
Thinner	:	T500
Recoat	:	6 hrs minimum 24 hours max
Aged Recoat	:	Sand Surface
Finish	:	Matt white

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.