



OceanMaster Marine Gloss Finish

Description

Premium single pack enamel finish having excellent durability, gloss and colour retention. Outstanding resistance to the marine environment.

For use on

A versatile conventional enamel suitable for all substrates. Above water-line application.

Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	:	N/A
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	76 microns
Dry Film Thickness	:	40 microns
Coverage	:	12 sq.m / L
Mixing Ratio	:	N/A
Thinner	:	T100 or T600
Drying Time	:	6 – 8 hrs
Recoat	:	18 hrs
Aged Recoat	:	Sand surface
Finish	:	Gloss

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.