



OceanMaster Marine Undercoat

Description

Surfacing undercoat with water resistance properties for above waterline applications. High opacity and good film build effectively hide substrate and level up minor surface imperfection.

For use on

Boat hulls after fairing, steel and aluminium after priming, or directly on fibreglass and timber. Provides excellent base for OceanMaster Marine Gloss and other similar coatings.

Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	:	N/A
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	90 microns
Dry Film Thickness	:	42 microns
Coverage	:	11 sq.m/L
Mixing Ratio	:	N/A
Thinner	:	T100 or T600
Drying Time	:	8 hrs
Recoat	:	16 hrs
Aged Recoat	:	Sand surface
Colour	:	Off White
Finish	:	Flat

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.