



OceanMaster Polygloss Finish

Description

The ultimate two-pack polyurethane finish that offers high gloss retention and chemical resistance. May be applied directly onto fibreglass gelcoat, epoxy or polyurethane undercoat.

For use on

Topside, deck, superstructure and any rigid construction after suitable surface preparation.

Direction for use

Product designed for application by spray or brush.

Airless Spray	Line Pressure :	100 – 130 Kg sq.cm
	Tip Size :	0.015 – 0.017
	Compression :	30:1
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	85 microns
Dry Film Thickness	:	40 microns
Coverage	:	11 to 12 sq.m/L
Mixing Ratio	:	3 to 1 by volume
Thinner	:	T300
Recoat	:	6 hrs min
Curing Time	:	48 hrs.
Aged Recoat	:	Sand Surface
Finish	:	Gloss

Health and Safety

Wear full acid protective gear including gloves and goggles. Use with adequate ventilation and do not use near naked flames.