



OceanMaster Etch Primer

Description

Two pack vinyl etch primer for pre-treatment of ferrous and non-ferrous metal except lead. It is designed only as a key coat and must be overcoated within the recommended time frame.

For use on

Suitable anti-corrosive primer for a wide range of substrates including steel and non-ferrous metals such as zinc, copper, bronze and aluminium. Not suitable for immersion application.

Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	:	Not recommended
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	40 microns
Dry Film Thickness	:	12 microns
Coverage	:	12.5 sq.m/L
Mixing Ratio	:	4 to 1 by volume
Pot Life	:	4 hrs @ 30°C
Thinner	:	Not required
Equipment Cleaner	:	Epoxy Thinner T500
Recoat	:	2 hrs min, 12 hrs max @ 30°C
Aged Recoat	:	Sand surface
Finish	:	Matt dark green

Health and Safety

Wear full acid protective gear including gloves and goggles. Use with adequate ventilation and do not use near naked flames.