



OceanMaster Everseal Epoxy Timber Preservative

Description

Two pack epoxy timber primer and sealer where the ultimate protection of bare timber is required. Low viscosity, high solids, coupled with preservative biocide ensures good penetration into wood to prevent dry rot.

For use on

All bare timber surfaces. Suitable as a clear undercoat prior to the application of any OceanMaster Varnish system.

Direction for use

Product designed for application by roller or brush.

First coat – add 50% thinner to saturate timber

Second coat – add 25% thinner to saturate timber.

Third and subsequent coats – no thinner required.

Wet Film Thickness	:	N/A
Dry Film Thickness	:	N/A
Coverage	:	06 - 16 sq.m / L (diluted)
Mixing Ratio	:	1 to 1 by volume
Thinner	:	T500
Drying Time	:	8 hrs
Recoat	:	02 hrs minimum and 12 hours maximum if applied wet on wet.
Aged Recoat	:	Sand surface
Finish	:	Clear

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.