



OceanMaster Hard Racing Xtreme Antifouling

Description

A hard matrix antifouling containing special additives offering a super smooth friction free surface.

For use on

All types of high speed vessels, vessels that are frequently in used or constantly on the move. Offers a smooth and low friction surface that minimizes drag, increases boat speed and fuel efficiency.

Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	Line Pressure :	200 Kg sq.cm
	Tip Size :	0.021 – 0.026
	Fan Angle :	65 to 80
Wet Film Thickness	:	120 microns
Dry Film Thickness	:	60 microns
Number of coats	:	2 coats (120 microns dry film)
Coverage	:	9 sq.m/L
Thinner	:	T100
Drying time	:	30 mins @ 30°C
Recoat	:	1 – 2 hrs min, max not critical but best within one week
Launch	:	4 – 6 hrs min, max not critical but best within 6 mths
Finish	:	White, Black, Blue

Health and Safety

Wear full acid protective gear including gloves and goggles. Use with adequate ventilation and do not use near naked flames.