



## OceanMaster *KRUISER* Self-Polishing Antifouling

### Description

An ablativ tin-free acrylic based antifouling. It's unique bio-active compound and self renewing effect makes it ideal for marine vessel operating in sever fouling conditions. Provides protection for 12 to 18 months when applied at the correct film thickness.

### For use on

Primed GRP, steel and timber hulls. Where long-life fouling protection reduces operating costs and extend dry docking intervals are required.

### Direction for use

Product designed for application by spray, roller or brush.

Airless Spray	Line Pressure	: 176 Kg sq.cm
	Tip Size	: 21 – 26
Conventional Spray		: N/A
Wet Film Thickness		: 140 microns
Dry Film Thickness		: 75 microns
Coverage		: 5 sq.m/L
Thinner		: T100
Drying Time		: 2 to 3 hours
Recoat		: 4 hours minimum. Maximum not critical. Best within 48 hours.
Launching		: 8 hours minimum. Maximum not critical. Best within 72 hours.
Finish		: Red, Black and Blue

### Health and Safety

Wear full acid protective gear including gloves and goggles. Use with adequate ventilation and do not use near naked flames.