



OceanMaster Universal Primer

Description

Two pack epoxy primer designed as an anticorrosive coating to provide excellent adhesion and water resistance prior to the application of heavy duty epoxy coatings such as OceanMaster Everguard Epoxy Undercoat.

For use on

Suitable for steel and non-ferrous metals such as zinc, copper, bronze and aluminum.

Direction for use

Product designed for application by spray, roller or brush.

| | | |
|--------------------|-----------------|-----------------------|
| Airless Spray | Line Pressure : | 120 Kg sq.cm |
| | Tip Size : | 0.015 – 0.021 |
| | Fan Angle : | 60 to 80 degrees |
| Conventional Spray | Pot Pressure : | 40 to 60 PSI |
| Wet Film Thickness | : | 85 microns |
| Dry Film Thickness | : | 40 microns |
| Coverage | : | 9 sq.m/L |
| Mixing Ratio | : | 3 to 1 by volume |
| Thinner | : | T500 |
| Recoat | : | 4 hrs min, 24 hrs max |
| Aged Recoat | : | Sand surface |
| Finish | : | Grey |

Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.