

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

Hard contact leaching heavy duty antifouling containing high percentage of copper and other toxic compounds offering protection from the greatest range of marine growth. Will withstand wiping and scrubbing down. Uses a anti slime technology for longer cleaner hulls

DIRECTIONS FOR USE

Usage

Primed GRP. Steel, timber and ferro cement hull
Not suitable for aluminium crafts.

Coverage

06 sqm/litre – 2 coats min. Additional coat along waterline, leading edges, keel & rudder

Mixing Ratio

3:1 by volume.

Recoating time

4-8 hours max

Thinner

Thinner: T100 (Max 10%)

Curing Time

N/A

Pack Sizes

1 Litre / 4 litres.

PRODUCT INFORMATION

Colour range : Black, Blue

QUICK TIPS

Product designed for roller / brush application

Key to ensuring a good job is to ensure proper surface preparation on various substrates before coating.

Use T500 thinner if necessary to degrease or wipe down surface prior to product application

Apply 02 coats of undercoat / primer before rolling on the Hard Racing Anti Slime. This is important for fibreglass / wooden decks where moisture might hinder proper adhesion of material. For metal surfaces, ensure 2 coats of anticorrosive primer before undercoat.

FULL RECOMMENDED SYSTEM

Everguard Epoxy Undercoat
Universal Primer (Anticorrosion)
Hard Racing Anti Slime Antifouling
T100 Thinner
T500 Thinner

160 MICRONS WET / 100 MICRONS DRY

**CONTACT US
TODAY
FOR PAINT ESTIMATES
AND TECHNICAL ADVICE**



OMI Coatings

102F Pasir Panjang Road #01-01
Citilink Warehouse Complex
Singapore 118530



T. +65 6777 6001
F. +65 6777 9006



omicoat.com
info@omicoat.com