HARD RACING

TECHNICAL DATA SHEET





PRODUCT DESCRIPTION

Hard contact heavy duty antifouling offering protection from the greatest range of marine growth. Will withstand wiping and scrubbing down. Offers super smooth friction free surface and reduces turbulence to increase speed or save fuel.

DIRECTIONS FOR USE

Usage

Primed GRP. Steel, timber and ferro cement hull Primed Aluminium surfaces

Coverage

06 sqm/litre - 2 coats min. Additional coat along waterline, leading edges, keel & rudder

Mixing Ratio

N/A

Recoating time

4-8 hours max. Launch within 14-21 days

Thinner

Thinner: T100 (Max 10%)

Curing Time

N/A

Pack Sizes

1 Litre / 4 litres / 20 litres

PRODUCT INFORMATION

Colour range : Black Blue Red Green

QUICK TIPS

Product designed for roller / brush application

Key to ensuring a good job is to ensure proper surface preparation on various substrates before coating.

Use T500 thinner if necessary to degrease or wipe down surface prior to product application Apply 02 coats of undercoat / primer before rolling on the Hard Racing. This is important for fibreglass / wooden decks where moisture might hinder proper adhesion of material. For metal surfaces, ensure 2 coats of anticorrosive primer before undercoat.

FULL RECOMMENDED SYSTEM

Everguard Epoxy Undercoat Universal Primer (Anticorrosion) Hard Racing Antifouling T100 Thinner T500 Thinner

160 MICRONS WET / 100 MICRONS DRY



T. +65 6777 6001

F. +65 6777 9006