



TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

Premium single pack enamel finish having excellent durability, gloss and colour retention. Outstanding resistance to the marine environment

DIRECTIONS FOR USE

Usage

Topside, deck, superstructure and any rigid construction after suitable surface preparation.

Coverage

12 sqm/litre – depending on usage & substrate

Mixing Ratio

Single pack

Recoating time

4-6 hours max

Thinner

T100 (25-30% Spray, 10-15% Brush)

Curing Time

48 hours, 07 days full cure

Pack Sizes

5 litres

PRODUCT INFORMATION

Aged Recoat : Sand Surface

Sand surface if time exceeds or when preparing for overcoating with a paint system

QUICK TIPS

Product designed for spray/ roller application

Key to ensuring a good job is to ensure proper surface preparation on various substrates before coating.

Use T500 thinner if necessary to degrease or wipe down surface prior to product application

Apply min 2 coats of MarineCoat Undercoat before rolling on the Marinegloss. This is important for fibreglass / wooden decks where moisture might hinder proper adhesion of material.

RECOMMENDED SPRAY GUN SETUP: BINKS

FLUID NOZZLE: 63-BSS 45-6321 (1.2MM)

FLUID NEEDLE: 563A 47-56310

AIR NOZZLE 63-P 46-6000

Wet Film Thickness: 76 Microns

Dry Film Thickness: 40 Microns

**CONTACT US
TODAY
FOR PAINT ESTIMATES
AND TECHNICAL ADVICE**



OMI Coatings

102F Pasir Panjang Road #01-01
Citilink Warehouse Complex
Singapore 118530



T. +65 6777 6001
F. +65 6777 9006



omicoat.com
info@omicoat.com