



TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

The ultimate two-pack, UV Resistant polyurethane finish that offers high gloss retention and chemical resistance. May be applied directly onto fibreglass gelcoat, epoxy or polyurethane undercoat.

DIRECTIONS FOR USE

Usage

Topside, deck, superstructure and any rigid construction after suitable surface preparation.

Coverage

12 sqm/litre – depending on usage & substrate

Mixing Ratio

3:1 by volume.

Recoating time

4-6 hours max

Sand surface if time exceeds or when preparing for overcoating with a paint system

Thinner

T300 (25-30% Spray, 10-15% Brush)

Curing Time

48 hours, 07 days full cure

Pack Sizes

1 Litre / 4 litre

QUICK TIPS

Product designed for spray/ roller application

Key to ensuring a good job is to ensure proper surface preparation on various substrates before coating.

Use T500 thinner if necessary to degrease or wipe down surface prior to product application

Apply min 2 coats of Everguard undercoat before rolling on the Polygloss. This is important for fibreglass / wooden decks where moisture might hinder proper adhesion of material. For metal surfaces, ensure 2 coats of Universal anticorrosive primer before undercoat.

RECOMMENDED SPRAY GUN SETUP : BINKS

FLUID NOZZLE: 63-BSS 45-6321 (1.2MM)

FLUID NEEDLE: 563A 47-56310

AIR NOZZLE 63-P 46-6000

Wet Film Thickness: 85 Microns

Dry Film Thickness: 40 Microns

**CONTACT US
TODAY
FOR PAINT ESTIMATES
AND TECHNICAL ADVICE**



OMI Coatings

102F Pasir Panjang Road #01-01
Citilink Warehouse Complex
Singapore 118530



T. +65 6777 6001
F. +65 6777 9006



omicoat.com
info@omicoat.com